

INTEX NL+ Neutral Automotive Silicone Sealant

Performance	Standard	Measured Value	Testing Method
Test at 50 RH and temperature 23 C:			
Density (g/cm ³)	±0.1	1.53	GB/T 13477
Skin-Free time Time (min)	≤180	12	GB/T 13477
Extrusion ml/min	≥150	650	GB/T 13477
Tensile Modulus(Mpa) 23C	≤0.4	1	GB/T 13477
	-20C or ≤0.6	3	GB/T 13477
Slumpability (mm) vertical	≤3	0	GB/T 13477
Curing Speed (mm/d)	2	3.2	GB/T 13477
As Cured after 21 days 50 RH and 23 C :			
Hardness (Shore A)	20~60	57	GB/T 531
Tensile Strength (Mpa)		2.5	GB/T 13477
Elongation of Rapture (%)		370	GB/T 13477
Movement Capability (%)	25	25	GB/T 13477
Shelf Life		15 months	