

KSD Neutral Autoglass Silicone Sealant

Performance	Standard	Measured Value	Testing Method	
Test at 50 RH and temperature 23 C:				
Density (g/cm ³)	±0.1	1.52	GB/T 13477	
Skin-Free time Time (min)	≤180	20	GB/T 13477	
Extrusion g/10s	≥150	12	GB/T 13477	
Tensile Modulus(Mpa)	23C	≤0.4	0.8	GB/T 13477
	-20C	or ≤0.6	1.8	GB/T 13477
Slumpability (mm) vertical	≤3	0	GB/T 13477	
Curing Speed (mm/d)	2	2.8	GB/T 13477	
As Cured after 21 days 50 RH and 23 C :				
Hardness (Shore A)	20~60	45	GB/T 531	
Tensile Strength (Mpa)		0.8	GB/T 13477	
Elongation of Rapture (%)		200	GB/T 13477	
Movement Capability (%)	12.5	20	GB/T 13477	
Shelf Life			15 months	