

PTK Multipurpose Polyurethane Sealant For Auto Windscrees:

Chemical base	1-C polyurethane
Colour (Appearance)	Black
Cure mechanism	Moisture curing
Non-sag properties(GB/T 13477.6)	Very good
Application temperature	5°C to 35°C
Tack-free time1 (GB/T 13477.5)	≤60mins
Curing speed (HG/T 4363)	see diagram
Shore A hardness (GB/T 531.1)	50~60 approx
Tensile strength (GB/T 528)	4 N/mm ² approx
Elongation at break (GB/T 528)	≥400%
Tear propagation resistance (GB/T 529)	≥8.0N/mm
Extrudability (ml/min)	40
Tensile-shear strength(MPa)GB/T 7124	3.5 N/mm ² approx
Service temperature	-40°C to 90°C
Shelf life (storage below 25°C) (CQP 016-1)	12 months