

GT Acetic General Silicone Sealant

Performance	Standard	Measured Value	Testing Method
Test at 50 RH and temperature 23 C:			
Density (g/cm3)	±0.1	0.94	GB/T 13477
Skin-Free time Time (min)	≤180	8	GB/T 13477
Extrusion ml/min	≥150	650	GB/T 13477
Tensile Modulus 23C	≤0.4	0.3	GB/T 13477
	-20C or ≤0.6	0.4	GB/T 13477
Slumpability (mm) vertical	≤3	0	GB/T 13477
Curing Speed (mm/d)	2	4	GB/T 13477
As Cured after 21 days 50 RH and 23 C :			
Hardness (Shore A)	10~30	15	GB/T 531
tensile Strength		0.3	GB/T 13477
Elongation of Rapture (%)		500	GB/T 13477
Movement Capability (%)	12.5	12.5	GB/T 13477
Shelf Life		12 months	