

P.T.K Neutral Automotive Silicone Sealant

Performance	Standard	Measured Value	Testing Method
Test at 50 RH and temperature 23 C:			
Density (g/cm ³)	±0.1	1.44	GB/T 13477
Skin-Free time Time (min)	≤180	30	GB/T 13477
Extrusion ml/min	≥150	318	GB/T 13477
Tensile Modulus(Mpa) 23C	≤0.4	1	GB/T 13477
	-20C or ≤0.6	2.5	GB/T 13477
Slumpability (mm) vertical	≤3	0	GB/T 13477
Curing Speed (mm/d)	2	3	GB/T 13477
As Cured after 21 days 50 RH and 23 C :			
Hardness (Shore A)	20~60	50	GB/T 531
Tensile Strength (Mpa)		2	GB/T 13477
Elongation of Rapture (%)		100	GB/T 13477
Movement Capability (%)	12.5	20	GB/T 13477
Shelf Life		15 months	