

SEVEN Acetoxy General Silicone Sealant

Performance	Standard	Measured Value	Testing Method
Test at 50 RH and temperature 23 C:			
Density (g/cm ³)	±0.1	0.935	GB/T 13477
Skin-Free time Time (min)	≤180	6	GB/T 13477
Extrusion ml/min	≥150	800	GB/T 13477
Tensile Modulus	23C ≤0.4	0.35	GB/T 13477
	-20C or ≤0.6	0.5	GB/T 13477
Slumpability (mm) vertical	≤3	0	GB/T 13477
Curing Speed (mm/d)	2	4	GB/T 13477
As Cured after 21 days 50 RH and 23 C :			
Hardness (Shore A)	10~30	23	GB/T 531
Tensile Strength (Mpa)		0.4	GB/T 13477
Elongation of Rapture (%)		600	GB/T 13477
Movement Capability (%)	12.5	12.5	GB/T 13477
Shelf Life		15 months	